

TECHNICAL DATA SHEET

Revision date: 12.09.2023

PRE-FILL 2K TO 1K CONVERTER

Article number:	25004
Colour:	depends on colour used
Intended use:	Car refinishing product/ repair.
General characteristics:	<p>Chamäleon Pre-fill 2K to 1K converter is prefilled with propellant and specific additives that converts 2K topcoats in a 1-component, physically drying paint. The Innovative spray and valve technology guarantee a broad jet with fine atomization, a high application rate and constant pressure for a professional result. The Chamäleon Pre-fill 2K to 1K converter is a can pre-filled with propellant gases, solvent and additives (275 ml) that can be filled with a 2K product (max. 100 ml) via a conventional (manual or pneumatic) filling machine.</p> <p>The converter converts 2K acrylic topcoat or HS topcoat into a 1K physically drying coat</p> <ul style="list-style-type: none">▪ High coverage▪ Simple, time-saving application▪ Excellent atomization▪ Light blending

Physical and chemical data:**Basis of binder:** acrylic resin**Smell:** solvent**Efficiency:** depending on consistence and colour of the substrate**Drying time at 20°C, 50% relative air humidity:** the drying time depends on surrounding temperature, air humidity, thickness of the applied coat and the type of paint used (refer to information from the paint manufacturer)**Size:** aerosol cans, maximum nominal volume 400 ml, filling quantity 100ml**VOC-value:** 214,7 g



CHAM'ALEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAM'ALEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

Application process:

Before use, carefully read and observe the warning texts on the label!

- Sand the surface to be painted and thoroughly clean with Chamäleon Silicone remover
- Larger bare surfaces must be primed with the appropriate Chamäleon primer
- The surface must be dry and free of dust and grease
- Shake can vigorously for 2 minutes
- Carry out spray test

For professional use only

Wear an appropriate respirator (recommended type A2/P3).

Storage stability:

If appropriate storage provided (=10°-25°C, relative air humidity max. 60%)

Unused cans: 5 years

Filled cans: depending on type of paint from several hours up to 6 month (information available from your paint dealer).

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.

STEUERNUMMER/TAX NR.: DE 231468544
EORI NR./CUSTOMS NR.: DE 6029442 / HRB 9778
GESCHÄFTSFÜHRER/CEO: SASCHA HAGEMANN

BANK HEIDELBERGER VOLKSBANK EG
IBAN DE78 6729 0000 0042 8627 03
BIC GENODE61HDI