



TECHNICAL DATA SHEET

Revision date: 30.10.2024

BASIC AEROSOLS: PRIMER

Article number:	26002, 26003, 26004, 26005
Colour:	black, white, grey, red
Intended use:	Car refinishing product/ Primer
General characteristics:	1K primer can be applied on various treated and untreated surfaces. Easy to sand, both wet and dry. <ul style="list-style-type: none">▪ prevents corrosion▪ excellent coverage▪ fast drying▪ re-sprayable with all lacquer systems
	Fields of application:
	<ul style="list-style-type: none">▪ metal▪ wood▪ aluminium▪ stone

TECHNICAL CHARACTERISTICS

Base: nitrocombi resin**Smell:** characteristic**Degree of gloss:** matt 10 ± 2 GU**Consumption:** 1.5 - 2 m² (500 ml)**DFT:** 15 - 30 µm**Temperature resistant:** up to 110°C

APPLICATION PROCESS

Before use, carefully read the directions on the packaging and act accordingly.

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +10 °C to +25 °C and max. air humidity should not exceed 80%.



Processing tips:

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers
- Beforehand, mask the parts that shouldn't be painted
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Apply the Primer in several thin layers
- Distance to the surface should be 25 - 30 cm
- Keep a flash off time 3 - 5 min between each spray pass (depending on the layer thickness)
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Dust free	Set to touch	Re-coatable
Object temperature 20 °C	5 - 10 min	10 - 20 min	2 h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max 675.6 g/l VOC

Shelf life:

120 months in tightly closed original container

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.