



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 12.06.2023

#### TECHNICAL DATA SHEET

# **2K AEROSOL CLEAR COAT PREMIUM**

Article number: 11012

Colour: transparent

**Intended use:** Car refinishing product/ Lacquer

General characteristics: 2K Aerosol clear coat premium is extremely scratch

resistant and provides high gloss and perfect resistance against fuel, UV-radiation and weather influences.

quick drying-time

excellent flow

easy polishing

• favourable 200 ml spray can to avoid paint residues

## **Application process:**

Before use, carefully read and observe the warning texts on the label!

**Substrate:** basecoats opaque or metallics

Preparation: after 30 min. air-drying time, basecoats can be re-coated with Chamäleon 2K Aerosol clear coat

premium

Spraying operations	DFT	Consumption
2-3 full spray passes	50 μm	

Flash-off time	Between the coatings	Before the oven drying
	approx. 2 min.	

	Drying	Polishing
Object temperature 20 °C	7 h	7 h
Object temperature 60 °C	25 min.	45 min.
IR-Drying	25 min.	30 min.



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE


## **Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

## Mixing of 2K Aerosol clear coat premium with hardener:







Remove protecting cap from the bottom of the can. Take out the ring and mount the ring through the whole of the bolt.

To mix the hardener with the A-component, place can upside down on even surface, then pull the bolt at the bottom of the can with the aid of the metal ring as far as it will go.

By a following  $360^{\circ}$  turn the cartridge will be completely opened and the hardener will be released. By the shaking of the can the component A will be mixed with the hardener with the exact, pe-determined mixing-ratio.

Spray to test

**Pot life:** 24 h 70°F (20°C)

#### **Important:**

#### For professional use only

#### The use of a respirator mask is necessary (recommended type A2/P3)!

This product contains isocyanate and can cause lung or breathing problems as well as hypersensitivity reactions. Before using or working with coating materials that contains isocyanate, all safety informations on the can label and the material safety data sheet must be read. Individuals with lung or breathing problems or prior reactions to isocyanate must not be exposed to vapour or spraymist.

Notice EU-safety data sheet as well as handling and warning notices on the label.

**Storage stability:** 36 months at 70°F (20°C) if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under: e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.

STEUERNUMMER/TAX NR.: DE 231468544 EORI NR./CUSTOMS NR.: DE 6029442 / HRB 9778 GESCHÄFTSFÜHRER/CEO: SASCHA HAGEMANN BANK HEIDELBERGER VOLKSBANK EG IBAN DE78 6729 0000 0042 8627 03 BIC GENODE61HD1