

TECHNICAL DATA SHEET

Revision date: 10.04.2025

AEROSOL LEATHER PAINT

| | |
|--------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Article number: | 26801 (black), 26808 (beige), 26809 (grey) |
| Colour: | black, beige, grey |
| Intended use: | Car refinishing product/ Paint |
| General characteristics: | <p>High quality leather spray to repair and embellish leather, vinyl and artificial leather parts.</p> <ul style="list-style-type: none">▪ lasting colour and lasting gloss▪ elastic▪ excellent adhesion▪ maintains the original structure |

TECHNICAL CHARACTERISTICS

Base: nitrocellulose**Smell:** characteristic**Gloss:** satin matt**Consumption:** 1.0 - 2.0 m² (400ml)**Temperature resistant:** up to 50°C

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +10 °C to +25 °C and max. air humidity should not exceed 80%.

Processing tips:

- The substrate must be clean, dry, free of dust and grease. Remove old loose coatings.
- Beforehand, mask the parts that shouldn't be painted
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)

- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Before use, test the compatibility of the surface
- Apply in several thin layers
- Distance to the surface should be 25 - 30 cm
- Keep a flash off time 3 - 5 min between each spray pass (depending on the layer thickness)
- Before applying the next layer, again shake the aerosol
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

| Drying | Dust free | Set to touch | Completely dry |
|--------------------------|------------|--------------|----------------|
| Object temperature 20 °C | 5 - 10 min | 10 - 20 min | 2 h |

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max. 682.2 g/l VOC

Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.