

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 30.07.2023

#### TECHNICAL DATA SHEET

## **LEATHER PAINT**

Article number: 26801

Colour: black

**Intended use:** Car refinishing product/ Colour spray for smooth leather

General characteristics: High quality leather spray to repair and embellish parts

of leather, vinyl and artificial leather.

Lasting colour and lasting gloss

Elastic

Excellent adhesion

Maintains the original structure

Surfaces: vinyl, leather and artificial leather

# Physical and chemical characteristics:

**Basis of binder:** nitrocellulose binder **Temperature resistance:** to 50 °C

Size: aerosol cans, maximum nominal volume 400 ml

Gloss: satin matt Coverage: 1-2 m<sup>2</sup>

**VOC-content:** approx..84% w/w **Solid content:** approx..16% w/w

### **Application process:**

Before use, carefully read and observe the warning texts on the label!

**Pretreatment:** the surface should be clean, dry and free of grease.

### **Treatment:**

- The surface should be clean, dry and free of grease.
- The aerosol should have room temperature. Best processing temperature 15 to 25°C.
- Before use, shake the aerosol for 2 minutes and spray a sample.



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

- Distance to the surface to be treated approx.. 25 30 cm.
- Apply the vinyl spray in several thin layers.
- Before applying the next layer, again shake the aerosol.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approx. 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### **Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

Drying	dust free	tack free	hardened/resprayable
Air drying 20 °C	5-10 min.	10-20 min.	after 2 h

# **Storage stability:**

10 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under: e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.