

TECHNICAL DATA SHEET

Revision date: 10.04.2025

AEROSOL UNDERBODY PROTECTION BITUMEN

Article number:	37100
Colour:	black
Intended use:	Car refinishing/ Anticorrosion product
General characteristics:	<p>High quality stone chip and corrosion protection for the underside and wheel wells of cars. The product has very good insulating and sound dampening properties. Can be applied to zinc coated surfaces if the correct primer is applied.</p> <ul style="list-style-type: none">▪ chemical resistance against: water, salt spray, oil, weak acids and bases▪ remains flexible▪ excellent corrosion prevention

TECHNICAL CHARACTERISTICS

Base: bitumen, solvents and waxes**Smell:** characteristic**Consumption:** 1.0 - 1.5m² (500 ml)**Temperature resistant:** -25°C to +80°C

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +15 °C to +25 °C and max. air humidity should not exceed 80%.

Processing tips:

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers.
- Beforehand, mask the parts that shouldn't be painted

- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Distance to the surface should be approx. 25 - 30 cm
- Apply in several layers
- Keep a flash off time 5 - 10 min between each spray pass (depending on the layer thickness)
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Dust free
Object temperature 20 °C	60 min

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied

VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max 545.3 g/l VOC

Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.