

TECHNICAL DATA SHEET

Revision date: 05.05.2025

AEROSOL PAINT FOR PLASTIC AND BUMPER

Article number:	26314 (grey), 26334 (black)
Colour:	grey, black
Intended use:	Car refinishing product/ Topcoat
General characteristics:	<p>High quality spray to repair and embellish plastic parts and bumpers with excellent adhesion.</p> <ul style="list-style-type: none">▪ perfect coverage▪ lasting colour and lasting gloss▪ scratch free and shock proof▪ resistant to chemicals and weather influences

TECHNICAL CHARACTERISTICS

Base: alkyd resin**Smell:** characteristic**Consumption:** approx. 1 m² (400 ml)**Temperature resistance:** up to 110°C

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +12°C to +25 °C and max. air humidity should not exceed 80%.

Processing tips:

- The substrate must be clean, dry, free from grease and dust
- Beforehand, mask the parts that shouldn't be painted
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature

- Before use, shake the aerosol for 2 min and spray a sample
- Apply several thin coats to get desired texture
- Distance to the surface should be 25 - 30 cm
- Keep a flash off time 3 - 5 min between each spray pass
- Before applying the next layer, again shake the aerosol
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Dust free	Set to touch	Completely dry
Object temperature 20 °C	20 - 30 min	60 min	24h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

VOC regulation:

EU limit value: Category B/e 840 g/l
contains max. 674 g/l VOC

Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.