

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440

FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 28.07.2020

TECHNICAL DATA SHEET

UNDERBODY PROTECTION WATER BASED

Article number: 37245 / 37246

Color: black / grey

Intended use: Car refinishing product/ the mixture Paint

General characteristics: Underbody Protection Water Based is a water-dilutable and

> environmentally friendly stone chip protection paint with sound absorbing properties. Suitable also as an insulating

primer with smooth surface.

Painting process:

Hardener: -

Dilution: ready to use, addition of up to 10% water possible

Spraying viscosity 4 mm DIN: thixotropic

Application process:

| Application parameter | Pressure | Nozzle | |
|-----------------------|---------------|----------------|--|
| Gravity spray gun | 2.0 - 2.5 bar | 1.3 - 1.5 mm | |
| HVLP | 2.0 - 2.2 bar | 1.3 - 1.5 mm | |
| Airmix / Airless | 100 - 120 | 0.33 - 0.50 mm | |
| UBS | 4 - 6 | 5 - 10 mm | |

| Spraying operations | DFT | Consumption | |
|---------------------|--------------|---------------------------|--|
| 2 | 100 - 300 μm | 2.5 - 5 m ² /l | |

| Flash-off time | Between the coatings | Before the oven drying | |
|----------------|----------------------|------------------------|--|
| | 5 - 8 min. | 10 - 15 min. | |

BANK HEIDELBERGER VOLKSBANK EG IBAN DE78 6729 0000 0042 8627 03 BIC GENODE61HD1

1



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440

FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

| Drying | | Dust free | Set to touch | Ready for assembly | Recoatable |
|--------------------|-------|---------------|--------------|--------------------|--------------|
| Object temperature | 20 °C | 25 - 30 min. | 30 – 35 min. | 24 h | 60 min. |
| Object temperature | 60 °C | | 10 – 15 min. | 1 h | 15 – 20 min. |

VOC regulation:

EU limit value: Category B/e 840 g/l This product contains max. 100 g/l.

Processing tips:

The substrate must be dry, clean and free from grease and rust. Pre-treat iron and steel surfaces to protect against corrosion. Sand slightly aluminium surfaces and old paintwork. The underbody must be cleaned thoroughly. It must be dry, free from dust, grease, oil and rust. Old non-adherent underbody coating must be removed. Mask beforehand motor, exhaust pipes, stub axles, cardan shaft and brake system as they must not be sprayed!

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under: email: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.