



TECHNICAL DATA SHEET

Revision date: 06.02.2025

AEROSOL CLEAR COAT PRO

Article number:	26407
Colour:	transparent
Intended use:	Car refinishing product/ Clear coat
General characteristics:	<p>Aerosol Clear Coat PRO is designed for quick coating and long-term sealing of repaired and newly painted surfaces. Thanks to its excellent elasticity, the product is especially suitable for application on soft and flexible components such as plastic parts.</p> <ul style="list-style-type: none">▪ quick drying time▪ excellent flow▪ good weathering resistance▪ UV protection▪ no colour deviation <p>Fields of application:</p> <ul style="list-style-type: none">▪ dried water- and solvent-based base coat systems▪ sanded, dry, intact topcoats (old and new)▪ various plastics (cleaned and sanded)

TECHNICAL CHARACTERISTICS

Base: acrylic resins

Smell: characteristic

Consumption: approx. 1 - 1.25 m² (500 ml)

DFT: 30 - 45 µm

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

■ **Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +12 °C to +25 °C and max. air humidity should not exceed 60%.

Processing tips:

- The substrate must be clean, dry, free from dust and grease
- Beforehand, mask the parts that shouldn't be painted
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature.
- Before use, shake the aerosol for 2 min and spray a sample
- Before use, test the compatibility of the surface and colour
- Apply Aerosol Clear Coat PRO in 2 - 3 full spray passes
- Distance to the surface should be 15 - 20 cm
- Process 1: apply 2 film forming spray coats with 5 - 10 min flash off time between each spray coat
- Process 2: apply 1 mist coat first, then after 1 - 2 min apply a closed, film-forming spray coat. If necessary, apply a further spray coat after 5 - 10 min
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Dust free	Set to touch	Completely dry
Object temperature 20 °C	5 min	40 min	24 h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

VOC regulation:

EU limit value: Category B/e 840 g/l
This product contains max 663 g/l VOC

Shelf life:

60 months, if stored in tightly closed original container

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.